izofalt yalıtım

Date of revision: June 26 2026
Revision number: 003

BİTÜWAP PUR 2K 8000 TECHNICAL SPECIFICATIONS


BITUMEN EMULSION AND ELASTOMERIC POLYURETHANE BASED, TWO COMPONENT LIQUID MEMBRANE

DESCRIPTION FOR IT

Bitumen emulsion and water-based elastomeric polyurethane-based, two-component, water-based, liquid waterproofing membrane with high crack-bridging ability, elasticity and tensile strength strengthened with various additives.

AREAS OF USE

It is used in underground waterproofing applications such as foundations, basements and curtains of buildings, and in the waterproofing of structures and building elements that are exposed to temporary and permanent water pressure. It is used in under-ceramic waterproofing of terraces, roofs, channels, kitchens, bathrooms, balconies and similar wet surfaces, and in the repair of old bituminous membrane coatings. When applied together with glass fiber, polyester felt and similar reinforcements, it provides long-lasting waterproofing against high pressure water.



APPLICATION SURFACES

It is suitable for application on mineral surfaces such as concrete, stone, plaster and screed in interior and exterior spaces.

ADVANTAGES

It can be applied to all mineral surfaces and has very high adhesion strength. Creating a seamless insulation layer. It can be applied very easily and quickly with the insulation pump. Resistance to underground chemicals.

APPLICATION CONDITIONS

Application should not be made in very hot or very humid weather. In applications, the ambient temperature should be between +5°C and +30°C. It should not be applied to melting, frozen surfaces or surfaces that are in danger of freezing within 24 hours. Repairs should be made before application to old mineral surfaces that are dusty

TOOLS USED

Insulation pump, brush, trowel or spatula.

SURFACE PREPARATION

If the surface to be applied is new, it must be free of residues such as cement residue and loose parts, oil, dirt, rust, algae and dust that prevent adhesion; It must be clean, smooth, solid and not exposed to frost. Inner corners should be chamfered with WAP TH – 602 repair mortar, and outer corners should be trimmed and rounded mechanically. The surfaces to be applied should be primed with BİTÜWAP PUR 2K 8000 diluted at a ratio of 1/5 (bitüwap pur 2k 8000 mixed liquid/water). BİTÜWAP PUR 2K 8000 should be applied as a skimming coat on perforated, damaged or porous surfaces with the help of a spatula or trowel in order to smooth the surface and prevent the formation of air bubbles. Old or dusty surfaces should be repaired and hardened with our POLYWAP IZK 6000 repair and impregination product.

APPLICATION

Bitüwap pur 2k 8000 should be opened from its packaging and mixed with a low-speed mixer for at least 1 - 2 minutes until it reaches a homogeneous consistency. It should be applied to the entire surface in 2 layers with the help of a brush or insulation pump. The total application thickness should be determined by looking at the rates in the consumption table according to the water pressure it will be exposed to. After the first coat application has dried completely, the second coat application should be started. In areas subject to temporary and permanent water pressure, in order to ensure an application thickness of 3 mm, glass fiber reinforcement mesh with a maximum weight of 100 g/m2 should be adhered to the entire surface before the first layer application dries and the second layer application should be started after it dries. The second layer application should be made to completely cover the net.

CONSUMPTION TABLE

Application area	Minimum application thickness (dry film)	Minimum consumption
Floor insulation that does not accumulate water	1,5 mm	2,5 kg/m²
Insulation against temporary pressurized water	2 mm (with glass fiber reinforcement mesh)	3,3 kg/m²
Insulation against continuous pressurized water	3 mm (with glass fiber reinforcement mesh)	5,0 kg/m²

TOOL CLEANING

All tools should be washed with water immediately after application. Dried residues should be cleaned with thinner.

PACKAGING

30 kg. Set (15 kg. + 15 kg.)

STORAGE AND SHELF LIFE

Stored in dry, moisture-free environments away from sunlight, provided the packaging is undamaged and unopened, the product has a shelf life of 12 months from the production date. Packaging must be protected from frost and heat. Two pallets should not be stacked on top of each other during transport and storage.

STANDARD

EN 1504 -2:2004 CE BELGESİ

TECHNICAL TABLE

PUR 2K 8000	TECHNICAL INFORMATION
The essence	The essence A)Bitumen Emulsion B)Polyurethane
Colour	Black
Form	Dark viscous liquid
Intersity	Average 1.15 gr/cm³
Softening point	80 Degrees
Installation period	Min. 3 Days
Waterproof	Class W1
Crack bridging capability	Class Cb2
Resistance to compression	Class C2A
Rain resistance	Class R1

WARNINGS AND RECOMMENDATIONS

It is not applied on metal surfaces. Water should never be added to the mixture. In applications made with an insulation pump, care should be taken to clean the machine installation immediately after the application is completed. Surfaces on which Bitüwap pur 2k 8000 has been applied should be covered within a maximum of 3 days and protected against external conditions. After the drying period, it should be covered with a suitable material. Earth filling should not be done without applying protection on the applied foundation shear walls. The application on the terrace should be solved by applying a thermal insulation layer over the waterproofing layer

SAFETY WARNINGS

Always use appropriate safety equipment such as masks, gloves, and goggles. Protect your eyes and face. Avoid contact with eyes and skin. In case of contact with eyes, rinse immediately with plenty of water and consult a specialist. For detailed safety information, please read the Material Safety Data Sheet.

LEGAL DISCLAIMER

İZOFALT Insulation Construction Textile Ind. And Trade Ltd. Co. İs not responsible for application errors that may occur if the product is used for purposes other than intended or if the above conditions are not complied with.